

Technical Information:

	Properties	Typical Values	Unit	Test Method
Physical	Color	Green	Visual	--
	Reinforcement Layer	Fiberglass	--	--
	Finish	Ripped	Visual	--
	Thickness	0.3 ± 0.03	mm	ASTM D374
	Operating Temperature	-40~+200	°C	--
Mechanical	Specific Gravity	1.20 ± 0.1	g/cm ³	ASTM D792
	Tensile Strength	70 ± 5	kgf/cm ²	ASTM D412
	Elongation	≥ 15	%	ASTM D412
	Hardness	60 ± 5	Shore A	ASTM D2240
	Coefficient of Friction	μ _s :1.72,SD:0.01	--	ASTM—D1894—01
Electrical	Voltage Breakdown	3000	V/mm	ASTM D149
	Volume Resistance	1.0 x 10 ¹³	Ω • cm	ASTM D257
Regulatory	RoHS Compliant	Yes	--	Lab. Certification

* The above testing results comes from laboratory report, information are for your reference only.