

Technical Information:

	Properties	Typical Values	Unit	Test Method
Physical	Color	Milky White	Visual	--
	Reinforcement Layer	--	--	--
	Finish	Smooth	Visual	--
	Thickness	0.3 ± 0.03	mm	ASTM D374
	Operating Temperature	-35~+180	°C	--
Mechanical	Specific Gravity	1.20 ± 0.1	g/cm ³	ASTM D792
	Tensile Strength	35 ± 3	kgf/cm ²	ASTM D412
	Elongation	≥ 180	%	ASTM D412
	Hardness	40 ± 5	Shore A	ASTM D2240
Electrical	Voltage Breakdown	4000	V/mm	ASTM D149
Regulatory	RoHS Compliant	Yes	--	Lab. Certification

* The above testing results comes from laboratory report, information are for your reference only.